

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : B01J 25/00, C07C 227/02	A1	(11) International Publication Number: WO 00/32310 (43) International Publication Date: 8 June 2000 (08.06.00)
(21) International Application Number: PCT/EP99/09267 (22) International Filing Date: 29 November 1999 (29.11.99) (30) Priority Data: 2387/98 1 December 1998 (01.12.98) CH (71) Applicant (for all designated States except AT US): NOVARTIS AG [CH/CH]; Schwarzwaldallee 215, CH-4058 Basel (CH). (71) Applicant (for AT only): NOVARTIS-ERFINDUNGEN VERWALTUNGSGESELLSCHAFT M.B.H. [AT/AT]; Brunner Strasse 59, A-1230 Vienna (AT). (72) Inventors; and (75) Inventors/Applicants (for US only): SIEBENHAAR, Bernd [DE/DE]; Obere Dorfstrasse 18, D-79400 Kandern-Wollbach (DE). RUSEK, Milos [CH/CH]; Tiefengrabenstrasse 49, CH-4102 Binningen (CH). (74) Agent: BECKER, Konrad; Novartis AG, Corporate Intellectual Property, Patent & Trademark Dept., CH-4002 Basel (CH).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: PROCESS FOR PREPARATION OF AMINOCARBOXYLIC ACIDS (57) Abstract Raney copper, which is doped (promoted) with an effective quantity of a doping (promoting) agent selected from the group boric acid, onium fluorides, salts of fluorine complex anions, and heteropoly acids, represents an outstanding oxidation catalyst for amine-group-containing primary amines to carboxylic acids.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Process for preparation of aminocarboxylic acids

The present invention relates to a process for the production of amine-group-containing carboxylic acid salts by oxidation of corresponding primary alcohols in an aqueous alkaline medium at an elevated temperature in the presence of a modified Raney copper catalyst.

In WO 92/06069, O. Gomez et al. describe the oxidation of ethanol amines to carboxylic acids, whereby the reaction is carried out in an aqueous-alkaline medium in the presence of Raney copper as the oxidation catalyst. In order to be able to reuse the catalyst in further reaction cycles, it must be reactivated, in this case by treatment with formic acid and then thorough washing with demineralised water and sodium hydroxide solution. Nevertheless, repeated usage is restricted because the catalyst has too short a service life and deactivates continuously.

In WO 94/24091, it is proposed that these disadvantages are remedied by doping (promoting) Raney copper with 10 to 50,000 ppm of an element or a metal, for example titanium, niobium, vanadium, molybdenum, manganese, nickel, lead and in particular chromium. The activity of the catalyst is only reduced thereby to a negligible extent. However, catalyst deactivation can be substantially improved. Of course, there is nothing to prevent the doping (promoting) metals, which are recognised as toxic, from reaching the reaction product, and after lengthy usage, the catalyst can no longer be reused. Simple reactivation is likewise impossible owing to the presence of doping (promoting) metals.

It has now surprisingly been found that the catalyst activity can be increased, the selectivity is maintained, the deactivation is only slight and, if necessary, can be eliminated by simple treatment with the doping (promoting) agent, and in this way multiple reuse in further reaction cycles is possible, and increased activity is observed in part during reuse, if the doping (promoting) agent employed is an ecologically acceptable agent, for example boric acid, onium fluorides or salts with fluorine complex anions, or heteropoly acids.

It was also surprisingly found that by adding adjuvants which contain carbaldehyde groups to the aqueous alkaline reaction medium, the catalyst activity and thus the reaction rate can be increased.

- 2 -

A first object of the invention is Raney copper, which is doped (promoted) with an effective quantity of a doping (promoting) agent selected from the group boric acid, onium fluorides, salts of fluorine complex anions, and heteropoly acids.

Effective quantity means that a minimum quantity is used and the effects are generally not further improved beyond the upper limit of a preferred quantity range. The minimum quantity, based on Raney copper, is preferably 10 ppm, more preferably 20 ppm and most preferably 50 ppm, and the maximum quantity is preferably 10,000 ppm, more preferably 8000 ppm and most preferably 5000 ppm.

Boric acid H_3BO_3 can be used as such in the treatment of Raney copper, or can be produced in the reaction medium from boric acid esters.

The onium fluorides in question may be, for example, unsubstituted or substituted phosphonium fluorides and more preferably ammonium fluorides. They may correspond to formula I,



wherein X is N or P and the symbols R are identical or different and signify H, C_1 - C_{20} -alkyl, C_2 - C_{20} -hydroxyalkyl, C_1 - C_4 -alkoxy- C_2 - C_{12} -alkyl, C_2 - C_8 -cycloalkyl, C_6 - C_{10} -aryl, C_7 - C_{12} -aralkyl or C_8 - C_{12} -alkaralkyl

R may be linear or branched alkyl, which preferably contains 1 to 12, more preferably 1 to 8, most preferably 1 to 4 carbon atoms. Examples are methyl, ethyl, and the isomers of propyl, butyl, pentyl, hexyl, heptyl, octyl, decyl, dodecyl, tetradecyl, hexadecyl, octadecyl and eicosyl. Alkyl is preferably linear and preferably denotes methyl, ethyl, n-propyl and n-butyl.

R may be linear or branched hydroxyalkyl, which preferably contains 2 to 12, more preferably 2 to 8, most preferably 2 to 4 carbon atoms. Examples are hydroxyethyl, hydroxypropyl and hydroxybutyl.

- 3 -

R as alkoxyalkyl preferably signifies C₁-C₄-alkoxy-C₂-C₄-alkyl, whereby alkoxy is most preferably methoxy or ethoxy. Preferred examples are methoxyethyl and ethoxyethyl.

R as cycloalkyl preferably contains 4 to 7, most preferably 5 or 6 ring carbon atoms. Examples of cycloalkyl are cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cycloheptyl and cyclooctyl. Cyclohexyl is especially preferred.

R as aryl may be naphthyl and preferably phenyl.

R as aralkyl is preferably phenylalkyl. Examples are benzyl and β -phenylethyl.

R as alkaralkyl preferably signifies alkylbenzyl, examples being methylbenzyl, dimethylbenzyl, trimethylbenzyl and ethylbenzyl.

X in formula I preferably signifies N.

One preferred group of compounds of formula I is that in which the symbols R are identical and are selected from the group H and C₁-C₄-alkyl. The compound of formula I in question is most preferably NH₄F.

Of the salts of fluorine complex anions, the alkali metal salts and onium salts are preferred in particular. Alkali metal salts are preferably, for example, lithium, sodium and potassium salts. Onium cations have already been described for the fluorides. The alkali metal salts may correspond to formula II,



wherein Me is NH₄⁺ or an alkali metal cation, preferably Li⁺, Na⁺ und K⁺, and Y signifies a perfluorine complex anion from the group BF₄⁻, AlF₄⁻, PF₆⁻, AsF₆⁻, SbF₆⁻ or BiF₆⁻. Preferred compounds are NaBF₄, KBF₄, NaPF₆, KPF₆ and especially NH₄BF₄ and NH₄PF₆.

The heteropoly acids are preferably derived from the poly-acid-forming elements W, Mo and V, whereby the polyanions contain elements from the groups P, B, Si and Ge. Heteropoly

- 4 -

acids are known and are described for example by I. V. Kozhevnikov in *Uspekhi Khimii* Volume 56, pages 1417 to 1443 (1987). Preferred heteropoly acids correspond to formula III,



wherein Z is P, B, Si or Ge, M is a metal from the group W, Mo and V, and n is an integer from 3 to 6. Preferred examples are $\text{H}_3[\text{P}(\text{W}_{12}\text{O}_{40})]$, $\text{H}_4[\text{P}(\text{W}_{12}\text{O}_{40})]$ and $\text{H}_5[\text{B}(\text{W}_{12}\text{O}_{40})]$.

The carbaldehyde-group-containing adjuvants are derived e.g. from formaldehyde, para-formaldehyde, the aliphatic C_1 - C_{12} -alkylcarbaldehydes, aromatic carbaldehydes and the corresponding dicarbaldehydes, whereby the aromatic rings may be substituted by C_1 - C_6 -alkyl or by OH. Of these, C_1 - C_6 -alkylcarbaldehydes, benzaldehyde, cuminaldehyde and 4-hydroxybenzaldehyde are preferred for example.

These carbaldehyde-group-containing adjuvants are conveniently employed in an amount ranging from 0.1 mol% to 50 mol%, preferably 1 mol% to 20 mol%, most preferably 2 mol% to 10 mol%, based on the primary amino alcohols of formula IV.

Production of the catalysts may take place in known manner, whereby an aqueous suspension of Raney copper is mixed with an aqueous solution of the modifying agent, the mixture is stirred or left to stand for a while, and then the impregnated Raney copper is filtered off or decanted and dried. The catalyst may also be produced and used *in situ*, whereby the aqueous mixture comprising catalyst and modifying agent is used directly after impregnation for the oxidation of primary alcohols. The catalyst may be used repeatedly. What is particularly advantageous here is that, when a loss of activity is first observed, further modifying agent is dispensed into the reaction mixture, and the loss of activity can be significantly to totally eliminated. In general, activated Raney copper is used for the modification. This is available commercially. Activation of Raney copper may be carried out whereby commercial Raney copper is treated for ca. 2 hours at a temperature of for example 200°C with a mixture of nitrogen and hydrogen (volume ratio for example 4:1), and is then cooled under a protecting gas (for example argon).

A further object of the invention is a process for the production of amine-group-containing carboxylic acid salts by oxidation of amine-group-containing primary alcohols in an

- 5 -

aqueous-alkaline reaction medium, in the presence of a modified Raney copper catalyst and at elevated temperature, the process being characterised in that the Raney copper is doped (promoted) with an effective quantity of a modifying agent selected from the group boric acid, onium fluorides, salts of fluorine complex anions and heteropoly acids.

The above-described embodiments and preferences apply to the modified Raney copper. The catalyst may be employed in a quantity of 0.1 to 30 % by weight, preferably 0.5 to 20 % by weight, more preferably 0.5 to 15 % by weight, most preferably 1 to 10 % by weight, based on the primary alcohol.


The reaction temperature may be for example from 80 to 300°C, preferably from 100 to 250 °C.

The reaction is advantageously carried out under excess pressure. The pressure may be, for example, from 1 to 50 bars, preferably 2 to 25 bars, most preferably 5 to 15 bars.

The reaction is carried out in an alkaline reaction medium, preferably in the presence of NaOH or KOH. The amount of alkali base in the reaction mixture is advantageously calculated such that at least equal molar amounts of alkali base are present in relation to the primary amine. It is appropriate to use an excess of alkali base, for example one to five times, preferably up to three times, most preferably up to double the molar excess.

The amines may contain 1 to 3 primary alcohol groups, and the amines may be primary, secondary or tertiary amines.

The amine-group-containing primary alcohols may correspond, for example, to formula IV,



wherein R_1 and R_2 , independently of one another, are H, linear or branched, C_1 - C_{18} -alkyl either unsubstituted or substituted by F, Cl, Br, $-NH_2$, C_1 - C_4 -alkoxy, C_1 - C_4 -halogenalkyl or

- 6 -

-COOH; C₃-C₈-cycloalkyl, C₆-C₁₀-aryl or C₇-C₁₂-aralkyl either unsubstituted or substituted by F, Cl, Br, -NH₂, C₁-C₄-alkyl, C₁-C₄-alkoxy, C₁-C₄-halogenalkyl; phosphonomethyl; R₁ and R₂ together are tetramethylene or pentamethylene; or R₁ and R₂, independently of one another, have the significance R₃-CH₂OH; and R₃ is linear or branched C₁-C₁₇-alkylene which is uninterrupted or is interrupted by C₃-C₈-cycloalkyl or C₆-C₁₀-aryl.

R₁ and R₂ as alkyl preferably contain 1 to 12, more preferably 1 to 8, most preferably 1 to 4 carbon atoms. Examples and preferences of alkyl have already been described.

R₁ and R₂ as cycloalkyl preferably contain 4 to 7, most preferably 5 or 6 ring carbon atoms. Examples of cycloalkyl are cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cycloheptyl and cyclooctyl. Cyclohexyl is especially preferred.


R₁ and R₂ as aryl may be naphthyl and preferably phenyl.

R₁ and R₂ as aralkyl are preferably phenylalkyl. Examples are benzyl and β-phenylethyl.

R₃ as alkylene preferably contain 1 to 12, more preferably 1 to 8, most preferably 1 to 4 carbon atoms. Examples of alkylene are methylene, 1,1- or 1,2-ethylene, 1,1-, 1,2- or 1,3-propylene, 1,1-, 1,2-, 1,3- or 1,4-butylene, 1,1-, 1,2-, 1,3-, 1,4- or 1,5-pentylene, 1,1-, 1,2-, 1,3-, 1,4-, 1,5- or 1,6-hexylene, 1,1-, 1,2-, 1,3-, 1,4-, 1,5-, 1,6- or 1,7-heptylene, 1,1-, 1,2-, 1,3-, 1,4-, 1,5-, 1,6-, 1,7- or 1,8-octylene, nonylene, decylene, undecylene, dodecylene, tridecylene, tetradecylene, pentadecylene, hexadecylene and heptadecylene.

The group -R₃CH₂OH preferably signifies 4-hydroxybutyl, 3-hydroxypropyl and most preferably 2-hydroxyethyl.

One preferred sub-group of compounds of formula IV corresponds to formula IVa,



- 7 -

wherein R_1 and R_2 , independently of one another, signify H or unsubstituted or $-NH_2$ or $-COOH$ -substituted C_1 - C_{12} -Alkyl or $-CH_2CH_2-OH$.

In formula IVa, R_1 and R_2 , independently of one another, preferably signify H, C_1 - C_4 -alkyl or $-CH_2CH_2-OH$. Another preferred sub-group is compounds of formula IVa, in which R_1 is $-CH_2CH_2-OH$ and R_2 , independently of one another, are H, C_1 - C_4 -alkyl or $-CH_2CH_2-OH$.

Some examples of compounds of formula IV are ethanolamine, diethanolamine, triethanolamine, N-methylethanolamine, N-dimethylethanolamine, N-methyldiethanolamine, N-ethylethanolamine, N-(n-propyl)ethanolamine, N-(n-propyl)ethanolamine, N-(n-butyl)ethanolamine, N-(n-pentyl)ethanolamine, N-(n-hexyl)ethanolamine, N-(n-octyl)ethanolamine, N-(n-decyl)ethanolamine, N-(n-dodecyl)ethanolamine, N-(n-tetradecyl)ethanolamine, N-(n-hexadecyl)ethanolamine, N-(n-octadecyl)ethanolamine, N-(di-n-propyl)ethanolamine, N-(di-n-butyl)ethanolamine, N-(di-n-hexyl)ethanolamine, 3-hydroxypropylamine, di-(3-hydroxypropyl)amine, tri-(3-hydroxypropyl)amine, 4-hydroxybutylamine, di-(4-hydroxybutyl)amine, tri-(4-hydroxybutyl)amine, 5-hydroxypentylamine, di-(5-hydroxypentyl)amine, tri-(5-hydroxypentyl)amine, 6-hydroxyhexylamine, di-(6-hydroxyhexyl)amine, tri-(6-hydroxyhexyl)amine, 8-hydroxyoctylamine, di-(8-hydroxyoctyl)amine, tri-(8-hydroxyoctyl)amine, 12-hydroxydodecylamine, di-(12-hydroxydodecyl)amine, tri-(12-hydroxydodecyl)amine, 18-hydroxyoctadecylamine, N-methyl-(3-hydroxypropyl)amine, N-methyl-(4-hydroxybutyl)amine, N-methyl-(6-hydroxyhexyl)amine, (2-aminoethyl)ethanolamine, di-(2-aminoethyl)ethanolamine, phosphonomethylethanolamine, diphosphonomethylethanolamine.

The compounds of formula IV are known, are partly commercially available or may be produced by processes that are similar to those described in literature.

The process according to the invention may be carried out, for example, in such a way that the catalyst is placed in an autoclave, then first of all the primary alcohol is added, optionally in water, followed by the alkali lye, the autoclave is sealed and the reaction mixture stirred, and the reaction is commenced whilst heating. The reaction generally continues until the hydrogen generation is no longer observed. The catalyst can be decanted from the cooled reaction mixture and used for the next reaction. The alkali metal salts of carboxylic acids that are formed may be isolated and optionally purified in the usual manner. The salts may also be converted into the free carboxylic acids and derivatives thereof, such as acid

amides and acid esters. The process according to the invention is suitable for production on an industrial scale.

The aminocarboxylic acids that may be produced according to the invention can be used for many purposes. Glycine is employed for food production. Aminocarboxylic acids are known complexing agents, which are used in the detergent industry and in water treatment. In addition, the amino alcohols may be used in the production of ionic surfactants. The amino alcohols are also valuable intermediates in the production of pharmaceutical and pesticidal compositions.

The following examples illustrate the invention more fully.

Example 1: Oxidation of diethanolamine

a) Preparation of the catalyst

A suspension of 8.26 g of activated Raney copper in 20 ml of water is stirred with 1.0 g of a 10% solution of NH_4B_4 in water, and then left to stand for 15 minutes. The whole mixture is subsequently transferred to a 300 ml nickel autoclave.

b) Oxidation of diethanolamine

To the catalyst are added 42.8 g of diethanolamine (0.4 moles), 20 ml of water and 38 g of NaOH (0.95 moles) in the form of a 50% aqueous solution. Afterwards, heating is effected to 160°C (9.5 bars, pressure regulating valve) and stirring takes place until the hydrogen generation is no longer observed (200 minutes). The yield of iminodiacetic acid disodium salt according to NMR analysis is more than 99% by weight.

c) Reuse of the catalyst

The autoclave containing the reaction mixture is cooled to 100°C. The supernatant solution is suctioned off through a riser, and the modified Cu catalyst remains in the autoclave. Then, diethanolamine and NaOH are added in the above-described proportions and reacted under the specified conditions. Up to the fifth reuse, the catalyst shows only slight activity loss (290 minutes, 92% by weight), and selectivity is maintained. Renewed impregnation with NH_4BF_4 gives a catalyst with the original high activity and selectivity.

Example 2: Oxidation of diethanolamine**a) Preparation of the catalyst**

A suspension of 8.26 g of activated Raney copper in 20 ml of water is stirred with 0.25 g of $H_3(PW_{12}O_{40})$ in 20 ml of water, and then left to stand for 15 minutes. The whole mixture is subsequently transferred to a 300 ml nickel autoclave.

b) Oxidation of diethanolamine

To the catalyst are added 42.8 g of diethanolamine (0.4 moles), 20 ml of water and 33.6 g of NaOH (0.84 moles) in the form of a 50% aqueous solution. Afterwards, heating is effected to 160°C (9.5 bars, pressure regulating valve) and stirring takes place until the hydrogen generation is no longer observed (3 hours). The yield of iminodiacetic acid disodium salt according to NMR analysis is 97% by weight.

c) Reuse of the catalyst

The autoclave containing the reaction mixture is cooled to 100°C. The supernatant solution is suctioned off through a riser, and the modified Cu catalyst remains in the autoclave. Then, diethanolamine and NaOH are added in the above-described proportions and reacted under the specified conditions. Up to the eighth reuse, the catalyst shows only slight activity loss (5 hours, 89% by weight), and selectivity is maintained. Renewed impregnation with $H_3(PW_{12}O_{40})$ gives a catalyst with the original high activity and selectivity (12th reuse, 3.5 hours, 91% by weight).

Example 3: Oxidation of diethanolamine**a) Preparation of the catalyst**

A suspension of 8.26 g of activated Raney copper in 20 ml of water is stirred with 0.25 g of NH_4F in 20 ml of water, and then left to stand for 15 minutes. The whole mixture is subsequently transferred to a 300 ml nickel autoclave.

b) Oxidation of diethanolamine

To the catalyst are added 42.8 g of diethanolamine (0.4 moles), 20 ml of water and 33.6 g of NaOH (0.84 moles) in the form of a 50% aqueous solution. Afterwards, heating is effected to 160°C (9.5 bars, pressure regulating valve) and stirring takes place until the

- 10 -

hydrogen generation is no longer observed (4 hours). The yield of iminodiacetic acid disodium salt according to NMR analysis is 98% by weight.

c) Reuse of the catalyst

The autoclave containing the reaction mixture is cooled to 100°C. The supernatant solution is suctioned off through a riser, and the modified Cu catalyst remains in the autoclave. Then, diethanolamine and NaOH are added in the above-described proportions and reacted under the specified conditions. Up to the twentieth reuse, the catalyst shows only slight activity loss (5 hours, 87% by weight), and selectivity is maintained. Renewed impregnation with NH_4F or dispensing in NH_4F during the reaction gives a catalyst with the original high activity and selectivity (21st reuse, 4 hours, 91% by weight).

Example 4: Oxidation of diethanolamine with the addition of benzaldehyde or 4-hydroxybenzaldehyde

a) Preparation of the catalyst

A suspension of 8.26 g of activated Raney copper in 20 ml of water is stirred with 0.25 g of NH_4F in 20 ml of water, and then left to stand for 15 minutes. The whole mixture is subsequently transferred to a 300 ml nickel autoclave.

b) Oxidation of diethanolamine

To the catalyst are added 42.8 g of diethanolamine (0.4 moles), 4.25 g of benzaldehyde or 4.9 g of 4-hydroxybenzaldehyde, 20 ml of water and 33.6 g of NaOH (0.84 moles) in the form of a 50% aqueous solution. Afterwards, heating is effected to 160°C (or 180°C) (9.5 bars, pressure regulating valve) and stirring takes place until the hydrogen generation is no longer observed.

Addition	Temperature (°C)	Duration of reaction (mins.)
benzaldehyde	160	210
benzaldehyde	180	67
4-hydroxybenzaldehyde	160	210
4-hydroxybenzaldehyde	180	53
none	160	270

- 11 -

The yield of iminodiacetic acid disodium salt according to NMR analysis is 97-98% by weight.

c) Reuse of the catalyst

The autoclave containing the reaction mixture is cooled to 100°C. The supernatant solution is suctioned off through a riser, and the modified Cu catalyst remains in the autoclave. Then, diethanolamine, 4-hydroxybenzaldehyde (or benzaldehyde) and NaOH are added in the above-described proportions and reacted under the specified conditions. Up to the twentieth reuse, the catalyst shows only slight activity loss, and selectivity is maintained. Renewed impregnation with NH_4F or dispensing in NH_4F during the reaction gives a catalyst with the original high activity and selectivity (21st reuse, duration of reaction 72 minutes, yield 92% by weight).

- 12 -

What is claimed is:

1. Raney copper, which is doped with an effective quantity of a doping agent selected from the group boric acid, onium fluorides, salts of fluorine complex anions, and heteropoly acids.
2. Raney copper according to claim 1, in which the minimum quantity of doping agent is 10 ppm, based on the Raney copper.
3. Raney copper according to claim 1, in which the maximum quantity of doping agent is 10000 ppm, based on the Raney copper.
4. Raney copper according to claim 1, in which the onium fluorides correspond to formula I,



wherein X is N or P and the symbols R are identical or different and signify H, C₁-C₂₀-alkyl, C₂-C₂₀-hydroxyalkyl, C₁-C₄-alkoxy-C₂-C₁₂-alkyl, C₂-C₈-cycloalkyl, C₆-C₁₀-aryl, C₇-C₁₂-aralkyl or C₈-C₁₂-alkaralkyl.

5. Raney copper according to claim 4, whereby the compound of formula I is NH₄F.
6. Raney copper according to claim 1, whereby the salts of fluorine complex anions are alkali metal salts of formula II,



wherein Me is NH₄⁺ or an alkali metal cation, and Y signifies a perfluorine complex anion from the group BF₄⁻, AlF₄⁻, PF₆⁻, AsF₆⁻, SbF₆⁻ or BiF₆⁻.

7. Raney copper according to claim 1, whereby the heteropoly acids are those of formula III,

- 13 -




wherein Z is P, B, Si or Ge, M is a metal from the group W, Mo and V, and n is an integer from 3 to 6.

8. A process for the production of amine-group-containing carboxylic acid salts by oxidation of amine-group-containing primary alcohols in an aqueous-alkaline reaction medium, in the presence of a modified Raney copper catalyst and at elevated temperature, whereby the Raney copper is doped with an effective quantity of a modifying agent selected from the group boric acid, onium fluorides, salts of fluorine complex anions and heteropoly acids.

9. Process according to claim 8, in which the catalyst is used in a quantity of 0.1 to 30% by weight, based on the primary alcohol.

10. Process according to claim 8, in which the amine-group-containing primary alcohols correspond to formula IV,



wherein R_1 and R_2 , independently of one another, are H, linear or branched, C_1 - C_{18} -alkyl either unsubstituted or substituted by F, Cl, Br, $-NH_2$, C_1 - C_4 -alkoxy, C_1 - C_4 -halogenalkyl or $-COOH$; C_3 - C_8 -cycloalkyl, C_6 - C_{10} -aryl or C_7 - C_{12} -aralkyl either unsubstituted or substituted by F, Cl, Br, $-NH_2$, C_1 - C_4 -alkyl, C_1 - C_4 -alkoxy, C_1 - C_4 -halogenalkyl; phosphonomethyl; R_1 and R_2 together are tetramethylene or pentamethylene; or R_1 and R_2 , independently of one another, have the significance R_3-CH_2OH ; and R_3 is linear or branched C_1 - C_{17} -alkylene which is uninterrupted or is interrupted by C_3 - C_8 -cycloalkyl or C_6 - C_{10} -aryl.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 99/09267

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 801J25/00 C07C227/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 801J C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 292 936 A (FRANCZYK THADDEUS S) 8 March 1994 (1994-03-08)	
A	EP 0 506 973 A (NIPPON CATALYTIC CHEM IND) 7 October 1992 (1992-10-07)	
A	US 3 928 441 A (HUNTER WOOD EUGENE ET AL) 23 December 1975 (1975-12-23)	
A	GB 642 861 A (REYNOLDS PETER W) 13 September 1950 (1950-09-13)	

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"B" document member of the same patent family

Date of the actual completion of the international search

2 March 2000

Date of mailing of the international search report

16/03/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Thion, M

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No.

PCT/EP 99/09267

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5292936 A	08-03-1994	AT 160770 T	15-12-1997
		AT 163403 T	15-03-1998
		AU 673260 B	31-10-1996
		AU 6627294 A	08-11-1994
		BR 9405924 A	12-12-1995
		CA 2121020 A	13-10-1994
		CA 2159828 A	27-10-1994
		CN 1120835 A	17-04-1996
		DE 69407082 D	15-01-1998
		DE 69407082 T	02-07-1998
		DE 69408662 D	02-04-1998
		DE 69408662 T	24-09-1998
		EP 0620209 A	19-10-1994
		EP 0694030 A	31-01-1996
		ES 2113648 T	01-05-1998
		GR 3026591 T	31-07-1998
		JP 2599570 B	09-04-1997
		JP 7002730 A	06-01-1995
		KR 174786 B	01-04-1999
		NZ 265493 A	28-10-1996
		WO 9424091 A	27-10-1994
		US 5367112 A	22-11-1994
		US 5739390 A	14-04-1998
EP 0506973 A	07-10-1992	AU 636803 B	06-05-1993
		AU 8711791 A	20-05-1992
		CA 2071999 A,C	24-04-1992
		DE 69115883 D	08-02-1996
		DE 69115883 T	05-06-1996
		DK 506973 T	29-01-1996
		ES 2081497 T	01-03-1996
		WO 9206949 A	30-04-1992
		JP 2916256 B	05-07-1999
		KR 9506892 B	26-06-1995
		MX 9101721 A	05-06-1992
		US 5220055 A	15-06-1993
US 3928441 A	23-12-1975	AU 471081 B	08-04-1976
		AU 7390574 A	08-04-1976
		BE 820956 A	11-04-1975
		CA 1030982 A	09-05-1978
		DE 2448603 A	17-04-1975
		FR 2247451 A	09-05-1975
		GB 1459016 A	22-12-1976
		JP 50088022 A	15-07-1975
		NL 7413371 A	15-04-1975
GB 642861 A		DE 846249 C	
		FR 992765 A	03-11-1951
		US 2604455 A	22-07-1952